SDL Packs

HIGH-BARRIER FILMS

Technical Data Sheet

VMCPP — Vacuum Metallized CPP Film

ISSUE DATE: 04 NOV 2026

DOCUMENT: TDS-VMCPP

TYPICAL SPECIFICATIONS

TEST ITEM	UNIT	TYPICAL VALUE	TEST STANDARD
Thickness	mic (Gauge)	25 (100) | 30 (120)	GB/T 6672-2001
Aluminum Adhesion (EAA)	N/15mm	0.5~1.0	Internal Method
Aluminum Layer Thickness (OD)	OD	2.0~2.2	Internal Method
Aluminum Layer Thickness	Å	400~440	Internal Method
Aluminum Layer Thickness	Ω/□	1.5~1.8	Internal Method
WVTR	g/(m²*24h), 90%RH, 38°C	0.6~0.8	GB/T 1037
OTR	cm³/(m²*24h*0.1Mpa), 23°C	8~15	GB/T 1038

NOTES

The data listed above are typical values obtained from standard tests and are provided for reference only. They do not constitute a guarantee of performance. Actual values may vary depending on substrate, coating weight, processing conditions, and test methods. For grade-specific requirements, please contact SDL Packs.

SDL Development Co., Ltd.
No. 6, Xinhe Road, Xieqiao Town, Haining, Zhejiang 314400, China
Website: https://www.sdlpacks.com | Email: sydshenchina@gmail.com | Tel: +86 134 5626 3964